


LUBRICATING OIL COMPOSITION FOR PAPER MACHINE**Publication number:** JP2002097485**Publication date:** 2002-04-02**Inventor:** TOMINAGA EIJI; KONISHI TORU**Applicant:** NIPPON MITSUBISHI OIL CORP**Classification:**

- International: C10M169/04; C10M129/10; C10M129/54; C10M129/76;
C10M133/12; C10M135/10; C10M135/24; C10M137/04;
C10M159/22; C10M159/24; C10N10/02; C10N10/04;
C10N30/04; C10N30/06; C10N30/12; C10N40/00;
C10N40/02; C10N40/04; C10N40/08; C10N40/30;
C10M169/00; C10M129/00; C10M133/00; C10M135/00;
C10M137/00; C10M159/00; C10M137/00; (IPC1-7):
C10M169/04; C10M129/10; C10M129/54; C10M129/76;
C10M133/12; C10M135/10; C10M135/24; C10M137/04;
C10M159/22; C10M159/24; C10N10/02; C10N10/04;
C10N30/04; C10N30/06; C10N30/12; C10N40/00;
C10N40/02; C10N40/04; C10N40/08; C10N40/30

- European:**Application number:** JP20000288492 20000922**Priority number(s):** JP20000288492 20000922**Also published as:** CN1213133C (C)**Report a data error here****Abstract of JP2002097485**

PROBLEM TO BE SOLVED: To obtain a lubricating oil composition for a paper machine which has good heat resistance and, at the same time, excellent corrosion resistance and wear resistance. **SOLUTION:** This lubricating oil composition for a paper machine comprises a base oil of at least one kind to be selected from a mineral oil, fats and oils, and a synthetic oil, (A) a phosphoric ester, (B) a phenol based antioxidant and/or an amine based antioxidant, and (C) an organic acid salt of at least one metal to be selected from an alkali metal, an alkaline earth metal, zinc, and lead.

Data supplied from the esp@cenet database - Worldwide